

<b>Physical Properties</b>	<b>ASTM</b>	<b>Value</b>
Color (Part A)		Various
Color (Part B)		Neutral
Color (mixed)*		Various
Consistency		Paste
Mix Ratio		1:1 by volume
Working Time**	CC881	30 Minutes
Full Cure Time**	CC881	8 Hours
Hardness, Shore D	D2240	75 [+/-5]
Conductivity		None
Compressive Strength, 7 days	D695	11,000 psi
Specific Gravity, mixed		1.27 g/ml
Bond Strength	C882	1,600 psi
Temperature Resistance		-20°F - 200°F
% VOC	EPA Method 24	0
<b>Slip Resistance, Wet***</b>	F609	0.71 (SCOF)

\*Standard Colors Black and Safety Yellow; Custom Colors Available

\*\*Based on Testing at 75°F (24°C)

Note: Lower temperature slows cure; higher temperature accelerates cure

\*\*\*Based on Tread Grit® HD (Heavy Duty) Application to Point of Refusal