



FORM-A-TREAD COMPANY
Division of RGF Materials Company (LLC)
37 Industrial Boulevard, Unit B
Paoli, PA 19301 USA
610-994-2138
www.form-a-tread.com

Form-A-Tread SL (Self Leveling)

DESCRIPTION

Form-A-Tread SL surface coating system combines a two-component, 100% solids, moisture-tolerant, low to medium viscosity, high strength, low modulus, multi-purpose liquid epoxy binder with topically applied, specialized colored aggregates. **Form-A-Tread SL** is extremely durable, UV resistant and provides increased traction, visibility, appearance, and safety on a variety of surfaces.

WHERE TO USE

Use **Form-A-Tread SL** on interior or exterior surfaces. It bonds to concrete, asphalt, steel, aluminum, wood, diamond plate, and other porous and non-porous surfaces. Use on ramps, crosswalks, demarcation areas, platforms, trailers, trucks, ships, walkways, loading docks, dock levelers, and any place a durable, decorative, high traction, and improved safety coating is needed.

ADVANTAGES

- High strength epoxy binder
- Extremely durable nonskid aggregate
- Easily Applied by hand
- Low maintenance
- Various aggregate colors and textures available
- Fast installation - open to traffic in 4 hours at 75°F.
- Convenient 1:1 mix ratio by volume
- Made in the USA

ESTIMATED COVERAGE

Epoxy Binder: 25 - 30 sq. ft. / gallon. Coverage varies depending on the texture of the surface.

PACKAGING

2-gallon Kit and 2 Cartons of Aggregate; 600ml Cartridge Packaging available on special order

EPOXY BINDER TECHNICAL DATA

Shelf Life:	2 years in original unopened container.
Storage Conditions:	40°F – 95°F (5°C – 35°C).
Condition material to:	65°F – 85°F (18°C – 29°C) before using.
Mix Ratio	1:1 by volume
Viscosity	1,500 cps @ 77°F
Gel Time (60 g mass)	15 minutes
Full Cure / Walk on Time (75°F or 23°C)	3 to 5 hours
Tensile Properties (ASTM D638), 7-day cure, Tensile Strength:	1,200 psi (8.3 MPa)
Tensile Properties (ASTM D638), 7-day cure, Elongation:	>75%
Bond Strength (ASTM C1583/ACI 503R)	300 psi (2.0 MPa), 100% substrate failure
Compressive Strength (ASTM C579), 3-hour cure:	2,500 psi (17.2 MPa)
7-day cure:	3,000 psi (20.7 MPa)
Flexural Strength (ASTM D790)	3,000 psi (20.9 MPa)
Shrinkage on Cure (ASTM D2566)	0.2%
Thermal Compatibility (ASTM C884)	Pass
Water Absorption (ASTM D570)	0.2% (24 hr.)
Dynamic Coefficient of Friction (DCOF), ANSI/NFSI B101.3-2012	0.76 (Hard Aggregate)

COLORED AGGREGATE PROPERTIES

The specialized colored aggregate used in the system provides a durable, high contrast, UV resistant, decorative and slip resistant surface.

Available colors: Grey, Yellow, HD (Heavy Duty) Plaza Mix (Other colors on special order)

CURE CHART

TEMPERATURE (°F)	50	70	90
WORKING TIME (minutes)	30	20	10
FULL CURE (hours)	12	5	2

SURFACE PREPARATION

Surface must be clean and sound. Surface should be visibly dry. No standing water. Concrete moisture levels must be less than 5 % when measured using a multi-pen moisture meter.

Surfaces should be abraded using 60 grit sandpaper, metal wire brush, diamond grinding wheel, or other similar materials to remove surface contaminants and increase mechanical bond. Polished concrete should be shot blasted to a CSP 3-5 per ICRI.

Dust, dirt, laitance, grease, curing compounds, impregnators, and other contaminants must be removed prior to installation for best bond.

Condition material to 65°F - 85°F (18-29°C) for optimum application. The minimum age of concrete is 30 days. The minimum age of asphalt is 30 days and 75% aggregate exposure.

APPLICATION

The colored aggregate and polymer resin binder shall be dispensed equally across the entire application surface in a manner that covers the surface area to be treated at the mil thickness of 50 - 60 mils without any breaks, swirls, ridge lines or differential thickness of the polymer resin binder over the area being treated. The colored aggregate shall simultaneously cover the polymer resin binder at a rate of 17 - 19 lbs. per square yard.

LIMITATIONS

Minimum substrate temperature is 50°F (10°C). Do not thin. Solvents will prevent proper cure.

CLEAN UP

Collect with absorbent material. Flush area with water. Dispose of in accordance with local, state and federal disposal regulations. Uncured material can be removed with acetone or other approved solvent. Cured material can only be removed mechanically.

LIMITED WARRANTY

All information provided, including but not limited to, any recommendations and advice relating to the application and use of the product is given in good faith based on current experience and product knowledge when properly stored, handled and applied under normal conditions in accordance with the instructions. We reserve the right to change the properties of its products without notice.

Prior to use the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Safety Data Sheet which are available at www.form-a-tread.com.

Form-A-Tread Company warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet when used in accordance with the written instructions. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY.